

Intrusion-Aid® DSC

Normal Range Water Reducing Grout Fluidifier

Description

Intrusion-Aid® DSC is a Normal Range Water Reducing Grout Fluidifier designed for use in augered cast-in-place piling grouts. Intrusion-Aid DSC provides a fluid grout with a dosage rate of approximately 5 pounds per cubic yard or 0.25 to 0.5 lbs per 100 lbs of cementitious.

Intrusion-Aid DSC also minimizes bleeding and setting shrinkage while maintaining a fluid, yet cohesive grout. When used at the recommended dosage rate, Intrusion-Aid DSC should eliminate the need for any additional admixtures in the grout.

Applications

- Augered Cast-in-Place Piles
- Conventional and Fabric Form Pile Jackets
- Erosion Control Mats and Fabric Forms
- Virtually Any Grouting Application

Features and Benefits

- Highly Fluid Grout
- Low Dosage Rate
- Eliminates Setting Shrinkage
- Virtually Eliminates Bleeding and Segregation

Applicable Standards

Intrusion-Aid FG meets U. S. Corps of Engineers Specification, CRD C-619, and ASTM Standard Specification for Grout Fluidifier, ASTM C-937.

Compatibility

Intrusion-Aid DSC Grout Fluidifier is compatible with most commercially available concrete admixtures. When used at the maximum dosage rate, no other admixture should be needed. The only exception could be extreme hot temperatures in which set time tests should be performed.

Performance Data

Time of Efflux (ASTM C-939)	20-25 secs
Water Retentivity (ASTM C-941)	passes
Bleeding (ASTM C-940)	0 %
Expansion (ASTM C-940)	3-4%
Time of Set (ASTM C-953)	Normal

Packaging

Intrusion-Aid DSC is packaged in 22.5 pound bags.

Storage

Intrusion-Aid DSC should be stored in a dry location protected from moisture and contamination. Intrusion-Aid Grout Fluidifiers are not subject to damage from freezing temperatures.

Precautions

Product is classified as a nuisance dust. Inhalation of dust may be harmful. Avoid repeated or prolonged breathing of dust. Use with adequate ventilation or with respiratory protection. In the event of exposure to dust, follow the precautions for nuisance dust and those detailed on the Material Safety Data Sheet.

Disclaimer and Limitation of Warranty

The information and recommendations contained in this publication are reliable and reflect the results of Specrete-IP's most current developments and tests. However, the appropriateness and suitability of specific uses and applications of any Specrete product, must be determined and verified by the user. Further, the successful application of any Specrete product, is critically dependent on user's following in all respects and details the recommended and industry standard procedures in preparation and application. Thus, as a consequence of the numerous factors on which successful application depends, Specrete-IP makes no warranties of any kind, express or implied, including those of merchantability and fitness for purposes and all claims including without limitation those sounding in breach of warranty, negligence, strict or product liability are limited to the purchase price of the material.